

SIGA 67ATG 7mm Excellence Range

SIGA 67ATG 7mm is a textured, blue/black slate, sourced from Spain. Its dark appearance makes it popular in Scotland and as one of our most versatile slates it can be used for most project types in Scotland including high profile and heritage projects.

The Excellence range of SIGA natural roofing slates is our widest range of slates offering a variety of sizes, colours and textures.

Due to the slate selection process, Excellence require minimal grading and sorting compared to Classic and Commercial Ranges.

All SIGA Excellence slates offer a 100 Year Warranty (T&C's apply)

Region Used: Scotland

Product Application: Conversion/Refurbishment, Housing Developments, Self Build, Heritage

Source: North West Spain

Colour: Blue/Black

Texture: Textured

Product Standard: BS EN 12326-1:2014

Thermal Cycling: T1

Exposure S02: S1

Water Absorption: W1



100 Year Warranty, T&C's apply. Must be registered for within 4 weeks of installation.

- Fix in accordance with BS 5534
- Full technical support and guidance is available
- Meets the requirements of NHBC
- CCPI Assessed 007600114/1126

Product Code	Thickness	Width	Length	Type	Coverage (Slates/m ²)
I0648307	7mm	200mm	300mm	Slate Blank	Headlap dependent
I0648306	7mm	200mm	300mm	Slate Holed 90mm	47.6
I0648308	7mm	300mm	300mm	Slate Blank	Headlap dependent
I0648310	7mm	200mm	350mm	Slate Blank	Headlap dependent
I0648309	7mm	200mm	350mm	Slate Holed 90mm	38.5
I0731127	7mm	220mm	350mm	Slate Holed 90mm	35
I0648311	7mm	300mm	350mm	Slate & Half Blank	N/A
I0731129	7mm	330mm	350mm	Slate Holed 90mm	23.3
I0731130	7mm	330mm	350mm	Slate & Half Blank	N/A
I0648313	7mm	200mm	400mm	Slate Blank	Headlap dependent
I0648312	7mm	200mm	400mm	Slate Holed 90mm	32.3
I0648315	7mm	220mm	400mm	Slate Blank	Headlap dependent
I0648314	7mm	220mm	400mm	Slate Holed 90mm	29.3
I0648317	7mm	250mm	400mm	Slate Blank	Headlap dependent
I0648316	7mm	250mm	400mm	Slate Holed 90mm	25.8
I0648318	7mm	300mm	400mm	Slate & Half Blank	N/A
I0648319	7mm	330mm	400mm	Slate & Half Blank	N/A
I0648320	7mm	370mm	400mm	Slate Blank	Headlap dependent
I0648322	7mm	250mm	500mm	Slate Blank	Headlap dependent
I0648321	7mm	250mm	500mm	Slate Holed 90mm	20.5
I0648324	7mm	370mm	500mm	Slate Blank	Headlap dependent

Slates are a natural product whose thickness/width/length can vary within supply standard tolerances. This variation impacts the quantity of slates that fit our non-returnable wooden packaging. Actual pallet weight and item count are included on the individual label for each pack.

Sorting & Handling

Natural slate should be handled with care. Before the slates are fitted they should be sorted and graded (and holed if necessary) as per BS 5534 and BS 8000. The factory selection of the slate used will have an impact on the amount of grading required.

The following processes should be followed to ensure best practice:

Sort slates into different thicknesses (thick, medium and thin). Thicker slates should be laid at the eaves, thinner slates at the ridge.

Any slate found to be twisted, bowed etc. should be set to one side and used for eave or top slates, or cut for half slates, valleys or chimneys.

Roofing slate is always holed from the back, creating a countersunk area on the front, so that any water present near the hole does not have a direct route to the underside of the slate. It also provides a neat spalled area for the nail head to sit in.

Pre-holed are supplied as standard in the UK. Unholed (blank) slates are also available to special order, and can give peace of mind on very low pitches when used with slate hooks.

Load out the slates on the roof with the thickest slates in the lowest courses.

Fixing

Fixing SIGA slate is straightforward for an experienced slater. They can be fixed by either traditional nailing, or by the modern hook system. Further fixing information is provided below - for a comprehensive guide, please refer to BS 5534.

Most SIGA slates come preholed at a nominal 90mm headlap. By simply moving the location of the slate on a standard 50x25mm batten, these can be fixed to obtain headlaps between 72 and 116mm, allowing them to be used on a variety of pitches.

Nail Size / Type For Tiles

Nail fixing is the traditional method of fixing slates and can be used for any slate apart from Galiza Brazilian. Most slates available from SIG are supplied pre-holed, with these pre-holed slates being holed from the reverse face creating a small countersink around the hole. This allows the nail head to sit flush with the slate.

To comply with BS 5534:

- The slate nails must be copper or aluminium and you would use 2 nails per slate. In corrosive or marine atmospheres copper nails are preferable and in severe conditions silicone bronze nails should be used.
- Nail Shank Diameter = 3.35mm
- Nail Shank Length = 20-25mm + 2x slate thickness (it needs to be long enough to penetrate the batten by 15mm)
- Nail Head Diameter = 10mm

Hook fixing

All natural slates can be hook fixed with "spike-end" nail-in hooks. Only this type of hook is permissible under BS 5534. Crimped spike-end hooks must be used at pitches of 30° or less. Hook fixings should not be used at pitches less than 25°. The hook method offers freedom in design and can reduce labour costs and eliminate breakages.

With hook fixings, the slate is held by the hook and 4 hooks are in contact with each slate, rather than just 2 nails with traditional fixing. This provides increased resistance to wind uplift. To comply with BS 5534, hook should be stainless steel 316 (marine) grade, 2.7mm gauge and at least 5mm longer than the minimum lap required.

Please refer to the SIGA brochure for more details regarding fixing, coverage, batten and holing gauges, headlaps and exposure.

British Standard

BS EN 12326-1:2014

On 31st January 2020 the United Kingdom officially left the European Union.

Prior to this Construction Products had been regulated under EU 305/2011 and its associated Harmonised European Standards.

The UK retained a form of Construction Products Regulation and in doing so assigned Designated Standards in support.

BS EN 12326-1:2014 covers Slate and stone for discontinuous roofing and external cladding - Part 1 Specification for slate and carbonate slate.

The conformity of a slate to the requirements of the Designated standard is stated in the associated Declaration of Performance (DoP).

The DoP lists the values from testing which the supplier declares in support of the products use and performance for a given application.

Actual test methods such as Thermal Cycling (Freeze/Thaw), Water Absorption etc. are described in BS EN 12326-2.